

缸砖和黏土

行业： 建筑材料， 化学

进料尺寸： < 25mm

最终精度：

样品量：

研磨建议：



VIBRATING CUP MILL PULVERISETTE 9

opt.speed

250 ml st.steel

Feed quantity: 350 g (250 ml)
Feed Size: < 3 cm
Grinding time: 10 min.
Final fineness: 95 % < 40 μ m
Comments: If hundred percent should be smaller than 40 μ m, just grind it five minutes longer.



VIBRATING CUP MILL PULVERISETTE 9

opt.speed

250 ml st.steel

Feed quantity: 120 g (100 ml)
Feed Size: < 100 μ m
Grinding time: 1 min.
Final fineness: 100 % < 50 μ m